



Mapesil™ T

100%-Silicone Sealant for Heavy Traffic and Movement Joints



DESCRIPTION

Mapesil T is a professional-grade, 100%-silicone sealant for use on multiple substrates. This product is specifically formulated for heavy traffic and expansion/movement joints exceeding both ASTM and ANSI standards.

FEATURES AND BENEFITS

- Color-matched to MAPEI's color palette
- Formulated to a low sheen to match the gloss of grout joints
- Rated for heavy-traffic and expansion/movement joints
- 100% silicone for use in interior, exterior, wet and dry installations from Res 1 to 6 and Com 1 to 6 as detailed per TCNA Environmental Classifications
- Excellent elongation and flexibility for use in both change-of-plane and joint applications in tile or stonework
- Can be used in pools and spas
- Helps to prevent mold and mildew

INDUSTRY STANDARDS AND APPROVALS

- ASTM: Meets C920, Type S, Grade NS, Class 25, Use T1, T2, NT, I, M, G, A and O, and conforms to C794 adhesion properties
- TCNA: Meets EJ171 requirements for heavy traffic and expansion/movement joints

LEED v3 Points Contribution

LEED Points

MR Credit 5, Regional Materials* Up to 2 points

IEQ Credit 4.1, Low-Emitting Materials –

Adhesives & Sealants1 point

IEQ Credit 4.3, Low-Emitting Materials – Flooring Systems.....1 point

** Using this product may help contribute to LEED certification of projects in the categories shown above. Points are awarded based on contributions of all project materials.*

WHERE TO USE

- Interior/exterior residential and commercial installations from Res 1 to 6 and Com 1 to 6 per TCNA Environmental Classifications
- As a flexible barrier/filler between horizontal/vertical surfaces and any other changes of plane
- Expansion joints in non-traffic, normal-traffic and heavy-traffic areas
- Countertops, vanities, sinks, bathtubs, showers, steam rooms, pools, spas, backsplashes and fixtures

LIMITATIONS

- Application temperature range is 40°F to 90°F (4°C to 32°C).
- Mapesil T may stain porous materials. Test a small area for staining or leaching before use to ensure compatibility with such porous materials as natural stone.
- Mapesil T should not be used in areas where material may come in contact with plasticizers or other materials that will prevent or diminish adhesion.
- Do not use Mapesil T for structural glazing.



- Not for use in expansion/movement joints with greater than 25% movement
- For joints with depth greater than 1/2" (12 mm), the caulking depth must be controlled by a closed-cell backer rod.
- Joint widths should not exceed 1" (2,5 cm).
- Although *Mapesil T* is color-matched to MAPEI's grout color system, expect a slight variation in color due to the difference in composition between materials.
- Not paintable; painting should be done before installation of *Mapesil T*.

SUITABLE SUBSTRATES

- *Mapesil T* adheres to most ceramic tile, porcelain, natural stone, glass, masonry, concrete, brick, wood, aluminum, fiberglass, vinyl, plastic, and properly prepared copper and brass.

Consult MAPEI's Technical Services Department for installation recommendations regarding substrates and conditions not listed.

SURFACE PREPARATION

- Surfaces must be structurally sound, stable, dry, clean and free from dust, oil, grease, paint, gypsum patch, flooring adhesive, tar, wax, sealers, curing compounds, form release agents, laitance, loose particles and foreign substances that could reduce or impair adhesion.
- All installation areas should be thoroughly cleaned mechanically or with a solvent as necessary and be firmly set before caulking. Typically, this is done 24 to 48 hours after tile installation.
- Remove all traces of loose paint, loose particles, residue and cement particles by mechanical means.
- Remove mildew by scrubbing with a mixture of 4 U.S. oz. (118 mL) of trisodium phosphate (TSP), 1 U.S. qt. (946 mL) of liquid bleach and 3 U.S. qts. (2,84 L) of warm water. Protect eyes and hands by wearing goggles and water/chemical-resistant gloves. Thoroughly rinse and allow the surface to dry completely before caulking and painting.
- Vacuum out joints and wipe them clean with a damp rag.

See MAPEI's "Surface Preparation Requirements" document in the Reference & Installation Guides section of the Tile & Stone Installation Systems page on MAPEI's Website.

MIXING

Choose all appropriate safety equipment before use. Refer to the Safety Data Sheet for details.

- *Mapesil T* comes ready to use.

PRODUCT APPLICATION

Read all installation instructions thoroughly before installation.

1. Caulking should take place after grout in the installation area has set.
2. For a clean, straight and neat sealant joint, mask both sides of the joint with masking tape.
3. Do not open the *Mapesil T* cartridge until preparatory work has been completed. Cut nozzle tip to the desired bead size at a 45-degree angle.
4. It will be necessary to insert a sharp tool (such as a screwdriver) inside the nozzle tip to puncture the protective aluminum foil seal inside the cartridge.
5. Apply *Mapesil T* with a caulking gun using steady, even pressure to completely bridge joints. Completely fill joints with sealant.
6. Tool the sealant using a "jointing tool" or the back of a spoon dipped in a solution of soapy water, to create a concave joint shape with a neat appearance.
7. Immediately after tooling the sealant, remove masking tape and wipe off any sealant from the face of the veneer with a paper towel before the material skins over. If the material skins over, excess sealant may need to be removed before curing with a commercial solvent.
8. Cured sealant will require mechanical means to remove.

PROTECTION

- Protect the installation area from traffic or water for at least 24 hours at 73°F (23°C).

Product Performance Properties

Laboratory Test	Results
VOCs (Rule #1168 of California's SCAQMD)	44 g per L
Slump (ASTM C639)	None
Tack-free time (ASTM C679)	20 to 25 minutes
Tooling time	5 to 10 minutes
Shore "A" hardness (ASTM C661)	38
Joint movement (ASTM C920)	+/-25%
Elongation at break (ASTM D412)	410%
Weatherability (Accelerated Weathering Tester QUV)	No change after 10,000 hours: Passes
Flexibility (ASTM C734)	Excellent: Passes at -15°F (-26°C)
Freeze/thaw stability: 0°F/77°F (-18°C/25°C) at 24 hours or ASTM C731	Passes 5 cycles

Protection and curing times will vary depending on ambient temperature, substrate temperature and humidity.

Shelf Life and Application Properties at 73°F (23°C) and 50% relative humidity

Shelf life	18 months when stored in original, unopened packaging
Full cure	28 days
Service temperature range	-60°F to 400°F (-51°C to 204°C)
Colors	Available in a variety of colors as well as clear

Packaging

Size
Cartridge: 10.1 U.S. oz. (299 mL)

Approximate Coverage* per 10.1 U.S. oz. (299 mL)

Joint Size	Coverage
3/8" x 3/8" (10 x 10 mm) by joint depth and width	11 lin. ft. (3,35 m)
1/4" x 1/4" (6 x 6 mm) by joint depth and width	25 lin. ft. (7,62 m)

* Coverage shown is for estimating purposes only. Actual jobsite coverage may vary depending on the joint size and application procedure.

Mapesil™ T

Refer to the SDS for specific data related to health and safety as well as product handling.

STATEMENT OF RESPONSIBILITY

Before using, user shall determine the suitability of the product for its intended use and user alone assumes all risks and liability whatsoever in connection therewith.

ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.

We proudly support the following industry organizations:



MAPEI Headquarters of the Americas

1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) /
(954) 246-8888

Technical Services

1-800-992-6273 (U.S. and Puerto Rico)
1-800-361-9309 (Canada)

Customer Service

1-800-42-MAPEI (1-800-426-2734)

Services in Mexico

0-1-800-MX-MAPEI (0-1-800-696-2734)

Edition Date: October 20, 2015

PR: 7656 MKT: 15-2110

For the most current **BEST-BACKED™** product data and warranty information, visit www.mapei.com.

All Rights Reserved. Printed in the USA. © 2015 MAPEI Corporation.